

SolidLux Adhesive 600

Product description

Solvent-free, transparent adhesive coat, to be finished with SolidLux Base Coat 800 and 900 and Top Coat 810, 810 AS and 910 AS.

Could also be used as adhesive improvement additive in the SolidLux Base Coat 800.

Cured by exposure to UV light.

- Realizes excellent adhesion on porous and highly absorbent surfaces
- Minimum disruption to floor users
- Immediately repaintable after curing
- Accessibility and use are disturbed as little as possible
- Solvent-free
- Can be applied in very low temperatures
- Easy to apply
- Cures independently of temperature
- Dual cure technology

Time is money: a SolidLux floor coating system can be applied with business being carried on as usual and minimum disruption to your workflow. Another important benefit – which cannot be expressed in monetary terms - is the customer satisfaction of residents, users and the public, due to the minimal disruption of access to (gallery) flats, parking garages or other public spaces. By following a carefully planned work order, temporary emergency provisions in many cases may not even be required.

Where can it be applied?

Can be used outside and inside, as a durable finish on any mineral surface.

As a coating for mechanically and chemically pressured (industrial) floors in warehouses, production areas, parking garages, balconies, galleries, outdoor terraces, stairs and workshops.

Useable on existing, undamaged epoxy or polyurethane based coatings.

Strictly to be used in combination with SolidLux Base Coat 900 or SolidLux Base Coat 800 and UV equipment approved by SolidLux.

Colour and packaging

1.25 and 2.5 kg container, transparent.

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication.

SolidLux Adhesive 600

Product performance and properties

Binder	UV-cured acrylate-based synthetic resin
Density at 20°C	approx. 1.15 kg/dm ³
Viscosity at 20°C	approx. 90 KU
Solids	approx. 100 volume %
Curing time	instantly ready for use after curing (exposure to UV light)
Adhesion strength	> 4.0 N/mm ² (concrete fracture) complies with required EN 1542 norm of 1.5 N/mm ² at min. (minimum required tensile strength for concrete surfaces)

Instructions for use

Application	Brush, wiper and roller
UV curing	Mobile UV curing installation or UV hand-held lamp Distance between the UV lamp and coating should be 35 mm
Speed of curing	max. 5 m ¹ per minute Over curing can be prevented by keeping the UV lamp in motion.
Dilution	Ready for use
Conditions of use	Temperature of surface must be at least 3°C above dew point to prevent condensation. Surface to be treated may contain a maximum of 4% moisture. Avoid direct sunlight (UV).

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication.

SolidLux Adhesive 600

Instructions for use (cont'd)

Attention points	<ul style="list-style-type: none">- Avoid exposure to sunlight (UV) by screening off the area.- Prepare surface to assure a clean and solid surface for good adhesion.- Use SolidLux Glue 630 for smooth and/or dense surfaces for an improved adhesion.- The available time for processing the mixture with SolidLux Adhesive 600 is 8 hours. After 8 hours the adhesive influence of SolidLux Adhesive 600 expires. Furthermore, can the mixture be processed normally. Re-adding more SolidLux Adhesive 600 to the mixture will not result in improved adhesion.- Mix coating mechanically before use and after pausing (slow rotation).- Apply with nylon roller (short pile, 6 mm).- Do not apply thicker coat than instructed (see theoretical coverage). Prevent thick layers.- Directly after application and tight flow cure coating by direct exposure to UV light.- When in doubt that coating is sufficiently cured, cure again with UV light.- After curing, directly apply pre-finishing coat of SolidLux Base Coat 800 or 900 and finish with 1 coat of SolidLux Top Coat 810, 810 AS or 910 AS.- SolidLux emits a typical odour.
Tool cleaning	Turpentine. No cleaning is required and can be reused if kept away from UV light
Theoretical coverage	At 130 micrometre dry coat thickness, approx. 7 m ² /kg (approx. 130 to 150 g/m ²)
Practical coverage	Depending on application method and structure of surface, 95% of theoretical coverage
Coat thickness	130 micrometre
Precautions	<p>Ensure adequate ventilation when applying and while drying. Use personal protection such as gloves, eye protection, suitable footwear and clothing.</p> <p>To protect the operator from direct exposure to UV light, a facial screen and complete skin protection must be worn during UV curing.</p> <p>More details and information can be found on the website of your supplier of UV equipment.</p>

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication.

SolidLux Adhesive 600

Health and environment

BREEAM



Fire certificate

The SolidLux system has the following classification with regard to its reaction to fire behavior in accordance with the standard EN 13501-1: 2007 + A1: 2009. The related product standard for the floor coating system is EN 13813: 2002.

- Fire behavior class Bfl
- Smoking behavior class s1



Flashpoint

≥ 100°C

Safety regulations

User is responsible for observing respective national regulations concerning safety, health and the environment.

For more information and current data consult the most recent version of the safety information sheet.

Article data

Storage

Store in cool, frost-free place

Maximum shelf life

6 months (in original, sealed packaging)

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication.