

SolidLux Base Coat 900

Product description

Solvent-free, opaque basecoat to be finished with SolidLux Top Coat 910 AS.
Cured by exposure to UV light.

- Minimum disruption to floor users
- Immediately repaintable after curing
- Accessibility and use are disturbed as little as possible
- Solvent-free
- Excellent adhesion to concrete
- Can be applied in very low temperature
- Suitable for anti-slip finish
- Impermeable
- Easy to apply
- Cures independently of temperature

Time is money: a SolidLux floor coating system can be applied with business being carried on as usual and minimum disruption to your workflow. Another important benefit – which cannot be expressed in monetary terms - is the customer satisfaction of residents, users and the public, due to the minimal disruption of access to (gallery) flats, parking garages or other public spaces. By following a carefully planned work order, temporary emergency provisions in many cases may not even be required.

Where can it be applied?

Can be used outside and inside, as a durable finish on any mineral surface.

As a coating for mechanically and chemically pressured (industrial) floors in warehouses, production areas, parking garages, balconies, galleries, outdoor terraces, stairs and workshops.

Usable on existing, undamaged epoxy or polyurethane based coatings.

Strictly to be used in combination with SolidLux Top Coat 910 AS and UV equipment approved by SolidLux.

Colour and packaging

Available in 5 and 10 kg containers in the following 13 industrial standard colours;

SL 1014, SL 3001, SL 3009, SL 5009, SL 6010, SL 6024, SL 7001, SL 7006, SL 7010, SL 7016, SL 7030, SL 7032 and SL 7037.

Other colours available on request.

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication

SolidLux Base Coat 900 (cont'd)

Product performance and properties

Binder	UV curing, acrylate-based synthetic resin
Density at 20°C	approx. 1.6 kg/dm ³
Viscosity at 20°C	approx. 90 KU
Solids	approx. 100 volume %
Curing time	Instantly ready for use after curing (exposure to UV light)
Adhesion strength	> 4.0 N/mm ² (concrete fracture) Complies with EN 1542 norm of 1.5 N/mm ² at min. (minimum required tensile strength for concrete surfaces)

Instructions for use

Application	Brush, wiper and roller
Anti-slip	Immediately after applying, sprinkle wet, 1 st coat of SolidLux Base Coat 900 sparingly with fire-dried sand, 0.3-0.8 mm (do not spread thickly). Usage 75 - 150 g/m ² . After applying the sprinkle and UV curing of the 1 st layer SolidLux Base Coat 900, will the amount of the 2 nd layer SolidLux Base Coat 900 be more, approx. 250 g/m ² .
UV curing	Mobile UV curing installation or UV hand-held lamp Distance between the UV lamp and coating should be 35 mm.
Speed of curing	max. 5 m ¹ per minute Over curing can be prevented by keeping the UV lamp in motion
Dilution	Ready for use
Conditions of use	Temperature of surface must be at least 3°C above dew point to prevent condensation. Surface to be treated may contain a maximum of 4% moisture. Avoid direct sunlight (UV).

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication

SolidLux Base Coat 900 (cont'd)

Instructions for use (cont'd)

Attention points	<ul style="list-style-type: none"> - Avoid exposure to sunlight (UV) by screening off the area. - Prepare surface to assure a clean and solid surface for good adhesion. - Use SolidLux Glue 630 for smooth and/or dense (coated) surfaces for an improved adhesion. - The available time for processing the mixture SolidLux Base Coat 900 with SolidLux Adhesive 600 is 8 hours. After 8 hours the adhesive influence of SolidLux Adhesive 600 expires. Furthermore, can the mixture be processed normally. Re-adding more SolidLux Adhesive 600 to the mixture will not result in improved adhesion. - Mix coating mechanically, before use and after pausing (slow rotation). - Apply with nylon roller (short pile, 6 mm). - Do not apply thicker coat than as instructed (see theoretical coverage). Prevent thick layers. - Directly after application and tight flow cure coating by direct exposure to UV light. - When in doubt that coating is sufficiently cured, cure again with UV light. - After curing, directly apply pre-finishing coat of SolidLux Base Coat 900 or finish with 1 coat of SolidLux Top Coat 910 AS. - SolidLux emits a typical odour.
Tool cleaning	Turpentine. No cleaning is required and can be reused if kept away from UV light
Theoretical coverage	At 100 micrometre dry coat thickness, approx. 6.5 m ² /kg (approx. 160 g/m ²)
Practical coverage	Depending on application method and structure of surface, 95% of theoretical coverage
Coat thickness	100 micrometre
Precautions	<p>Ensure adequate ventilation when applying and while drying. Use personal protection such as gloves, eye protection, suitable footwear and clothing.</p> <p>To protect the operator from direct exposure to UV light, a facial screen and complete skin protection must be worn during UV curing.</p> <p>More details and information can be found on the website of your supplier of UV equipment.</p>

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication

SolidLux Base Coat 900 (cont'd)

Health and environment

BREEAM



Fire certificate

The SolidLux system has the following classification with regard to its reaction to fire behavior in accordance with the standard EN 13501-1: 2007 + A1: 2009. The related product standard for the floor coating system is EN 13813: 2002.

- Fire behavior class Bfl
- Smoking behavior class s1



Flashpoint

≥ 100°C

Safety regulations

User is responsible for observing respective national regulations concerning safety, health and the environment.
For more information and current data consult the most recent version of the safety information sheet.

Article data

Storage

Store in cool, frost-free place

Maximum shelf life

6 months (in original, sealed packaging)

The information contained in this product information sheet was current at the time of printing. Information on this product is regularly updated and subject to change without prior notice. Lowland Coatings International B.V. rejects any liability other than willful intent or gross negligence where a loss is ascribed to inaccuracy or incompleteness of the information obtained via this publication